

Dekguard E2000

High performance elastomeric anti-carbonation protective and decorative coating for concrete and masonry

Uses

Dekguard E2000 is designed to protect atmospherically exposed, reinforced concrete structures (above any splash zones) from attack by carbonation, chloride ions, oxygen and moisture ingress, especially where there is a danger of subsequent cracks appearing within the substrate. Typical uses include, but are not necessarily limited to, the following:

- Anti-carbonation coating for new and existing structures
- Concrete storage tanks - external surfaces
- Bridge structures
- Coastal environments

Advantages

- **Crack accommodation** - withstands substrate cracking up to 2 mm and cyclic movement up to 1 mm.
- **High performance** - comprehensive barrier against carbon dioxide, water, sulphates and chloride ions.
- **Extremely durable** - maintains elastomeric performance, with high recovery, even after long term UV weathering.
- **Breathable** - water vapour can escape from the structure.

Description

Dekguard E2000 is an aliphatic acrylate elastomeric, water-based protective coating based on a special acrylic polymer. It provides excellent elongation and recovery, resistance to aggressive elements, UV light and rain. It is available in a wide range of colours.

Design criteria

To achieve the desired protective properties, the Dekguard E2000 must be applied to the substrate at the correct coverage rates. The coating should thus be applied in two coats to achieve a total dry film thickness of not less than 200 microns.

Specification

Where shown on the contract documents, the protective coating system shall comprise the following elements:

- (i) a single component, elastomeric, aliphatic acrylic coating (Dekguard E2000), 2 coats.

The total dry film thickness of the protective coating system shall be not less than 200 microns, and shall provide:

- (a) CO₂ diffusion resistance equivalent to not less than 125mm of 30 N/mm² concrete cover or 50 m of air cover (Taywood method).
- (c) A water vapour transmission resistance (S_D) of not more than 0.32 metres (Taywood method).
- (d) Static crack accommodation of not less than 2mm (BRE).
- (e) Adhesion greater than 1.0 N/mm² as per BS 1881

Properties

The values obtained are for the Dekguard E2000 applied at the minimum recommended application rate.

Solids by weight:	64
Volume solids:	50%
Carbon dioxide diffusion resistance Equivalent thickness of air (Taywood method):	> 175 metres
Carbon dioxide diffusion resistance Equivalent thickness of 30N conc. (Taywood method):	> 500 mm
Water vapour diffusion resistance: (Klopfer method - eff. resist. S_D < 4m) Taywood method):	S _D 1.0 @ 200 microns dft
Chloride ion diffusion coefficient: (Taywood method)	No chloride ion diffusion after 60 days
Static crack spanning capability @ 200 microns dft @23°C: (modified ASTM C836-76)	2 mm
Tear resistance (ASTM D1004-76):	15 N/mm
Tensile Strength (ASTM D412-87):	5.0 N/mm ²
Reduction in Water absorption (ASTM C642):	> 82%
Reduction in chloride ion penetration (AASHTO M259):	> 92%
Adhesion (BS 1881):	1.0 N/mm ²

Dekguard E2000

Instructions for use

Application over existing membranes and/or coatings

It is not necessary to remove Fosroc's Nitobond AR or Concure A prior to the application of Dekguard E2000.

However, for all other types of membrane or coating; it is advisable to carry out trials to determine both compatibility with Dekguard E2000, and retention of bond between the underlying coating or membrane and the substrate. For further advice, contact the local Fosroc office.

Substrate preparation

All surfaces should be dry and free from contamination such as oil, grease, loose particles, decayed matter, moss, algal growth, laitance, and all traces of mould release oils. This is best achieved by lightly grit-blasting the surface to the point where the fine aggregates are exposed but not polished. Where moss, algae or similar growths have occurred, treatment with a proprietary biocide should be carried out after the grit-blasting process.

It is essential to provide an unbroken coating of Dekguard E2000. Thus all blow holes and similar surface irregularities should be filled using Renderoc FC and should be allowed to cure properly before the application of Dekguard E2000. Consult the local Fosroc office for further details.

Substrate priming

Priming is not normally required provided that the substrate is concrete is sound and of good quality, low permeable and non-porous.

For low permeability concrete, non-porous and having w/c ratio < 0.4, no primer is required.

If concrete is pours, w/c ratio >0.4 or if the concrete expected to have relative humidity > 75%, a primer coat is required to 'stabilise' the substrate. The depth of penetration of the primer, and thus its coverage rate, are determined by substrate profile, porosity and general condition.

For masonry substrates, primer is required.

The primer shall be Dekguard Primer DG, a film-forming, stabilizing primer which is supplied as a clear liquid and is based on an acrylic resin and a silane-siloxane dissolved in a penetrating organic carrier. The primer is reactive and capable of producing a chemically-bound hydrophobic barrier, thus inhibiting the passage of water and water-borne contaminants. A thin surface film is produced which consolidates and stabilises porous substrates.

The primer is best applied by using portable spray equipment e.g. knapsack-type. A uniform surface appearance (sheen) should be apparent when the required rate of application rate has been achieved. If any matt, porous patches remain, then a further application of Dekguard Primer DG should be made.

If in any doubt regarding substrate priming, contact the local Fosroc office.

Any areas of glass should be masked. Plants, grass, joint sealants, asphalt and bitumen-painted areas should be protected during application.

Application

The correct application rates and over-coating times should be observed, in order to obtain the complete benefits of the protective properties of the Dekguard E2000, except where substrate condition dictates different application rates for the primer.

Dekguard Primer DG (conditional)

Number of coats	1
Theoretical application rate per coat:	4m ² per litre
Theoretical wet film thickness per coat:	N/A
Over-coating time: @ 20°C 2 hours	2 hours
@ 35°C 1 hour	1 hour

Where primer is required, it should be allowed to dry for a minimum of 2 hours at 20°C (or 1 hour at 35°C) before application of Dekguard E2000. Under no circumstances should the primer be over-coated until the surface is properly dry.

Dekguard E2000

Number of coats	2
Theoretical application rate per coat:	5m ² per litre
Theoretical wet film thickness per coat:	200 microns
Over-coating time: @ 20°C 2 hours	When firm to the touch
@ 35°C 1 hour	

Dekguard E2000 should preferably be applied by airless spray equipment, but can also be applied by roller. For further information about application techniques and equipment consult the local Fosroc office.

All prepared substrates should be treated with two coats of Dekguard E2000. It is important that no gaps or 'raw edges' appear in the finished coating. Special care should be taken to provide an unbroken coating at external corners and similar exposed protrusions.

The first coat should be applied to achieve a uniform coating with a wet film thickness not less than 200 microns. This coat should be allowed to dry until firm to the touch. Typically, this will be after approximately 12 hours in dry weather at 35°C.

Prior to application of the second coat, a close visual inspection of the surface should be made to check for any pin holes or surface irregularities. Any such irregularities should be filled with Dekguard Filler, and allowed to dry before proceeding.

Dekguard E2000

The second coat of Dekguard E2000 should be applied at 90° to the first, to ensure a final full unbroken coating to the substrate. The second coat should once more be applied at a wet film thickness of not less than 200 microns.

In order to maintain a record of the coating activities a coating log should be kept.

Cleaning

Dekguard E2000 and Dekguard Filler should be removed from tools and equipment with clean water immediately after use. Dekguard Primer DG should be removed using Fosroc Solvent 102.

Limitations

Where application over existing sound coatings or paints is required, trials should be conducted to ensure compatibility and retention of the bond between the underlying coating and the substrate. Compatibility and soundness should be assessed on a trial area.

Dekguard E2000 should not be used in submerged or permanently wet conditions. Consult the local Fosroc office for recommendations.

Application should not commence if the temperature of the substrate is below 20°C or above 60°C, or where the prevailing relative humidity exceeds 90%.

In conditions of high relative humidity i.e. 85-90% good ventilation conditions are essential. Substrate temperature should be at least 3°C above dew point.

Dekguard E2000 should not be applied in windy conditions where early-age dust adhesion may occur, or where rain is likely within 2 hours.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Dekguard Primer DG:	20 litre drums
Dekguard E2000:	20 litre drums
Dekguard Filler:	18 litre drums
Renderoc FC:	20 kg bags
Fosroc Solvent 102:	4 litre drums

Coverage

Dekguard Primer DG:	4.0 m ² per litre (total)
Dekguard E2000:	2.5 m ² per litre (total)
Renderoc FC:	Approximately 12.0 litres per 20 kg bag (4.0 m ² at 3 mm thickness)

Note: The coverage figures given are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Application rates and coverage of Dekguard E2000 may be varied according to particular service conditions. However, to ensure that the desired performance properties of the material are attained, it is important to observe correct application procedure.

Storage

When stored in cool, dry conditions, away from sources of heat and naked flames, in the original, unopened packs, all products have a shelf life of 12 months.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Dekguard E2000 should be protected from frost.

Precautions

Health and safety

Dekguard Primer DG, Dekguard E2000 and Fosroc Solvent 102 should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to alkalis, resins and solvents.

Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - **do not** induce vomiting.

Fire

Dekguard E2000, Dekguard Filler and Renderoc FC are non-flammable.

Dekguard Primer DG and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO₂ or foam. Do not use a water jet.



Dekguard E2000

Flash points

Dekguard Primer DG:	38°C
Fosroc Solvent 102:	33°C

For further information, refer to the Product Material Safety Data Sheet.

Additional information

Hot weather working practices

Whilst the performance properties of Dekguard E2000 at elevated temperatures are assured, application under such conditions can sometimes be difficult. It is therefore suggested that, for temperatures above 35°C, the following guidelines are adopted as a prudent working regime:

- (i) Store unmixed materials in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- (ii) Keep application equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- (iii) Try to eliminate application in the middle of the day, when ambient temperatures will be excessively high.
- (iv) Ensure that there are sufficient operatives available to complete application within the pot life of the material.
- (v) Have a ready supply of Fosroc Solvent 102 available for immediate cleaning of tools after use.



Fosroc Vietnam Limited

Factory & Head office

Unit 1, Block 18, Ninh Logistics Park
No. 1 Street 6
VSIP Bac Ninh Industrial Park
Phu Chan Commune Tu Son Town
Bac Ninh Province Vietnam

www.fosroc.com

Important note:

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:

+84 (0) 241 3765 971/2

fax:

+84 (0) 241 3765 973

Fosroc Vietnam Limited Investment Certificate 212 043000 519, Issued on 18.04.2013; 1st revision 27.02.2014