

# Fosroc® Renderoc Plug

## Rapid setting cement-based, water-stopping mortar

### Uses

For the rapid temporary patching and plugging of concrete segments, concrete and brick tunnel linings, sewage systems, below ground access chambers, pipes, basements, foundations, and mines.

### Advantages

- Emergency, water-stopping capability
- Single component– only the addition of clean water is required.
- Excellent bond to the substrate
- Low exotherm minimizes thermal cracking
- Pre-bagged formulation to overcome variations in site batching
- Contains no chloride admixtures

### Description

Renderoc Plug is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent, rapid setting mortar which is easy to apply in many difficult conditions. The material is based on a blend of cements, graded aggregates, special fillers and chemical additives which control the rate of set and minimize the risk of thermal cracking.

Renderoc Plug provides an initial set time of approximately one minute.

### Design criteria

Renderoc Plug can be applied to horizontal, vertical or overhead surfaces at a wide range of thicknesses. Generally, the volume of mixed material used in a single application is restricted to that which can be applied by trowel or gloved hand. Thicker sections can be built up in layers. If any doubt arises about the nature of the substrate, consult the local Fosroc office for further information.

### Typical properties

Following results obtained @ 23 ±2°C

Compressive strength	: 5 N/mm <sup>2</sup> @ 2 hours
(BS 6319 Pt 2: 1983)	32 N/mm <sup>2</sup> @ 28 days
Initial set time	: 1 - 3 minutes

**Note:** Set times will be extended when mixed at lower temperatures.

### Specification

Water stopping mortar

The water-stopping mortar shall be Renderoc Plug, a single component cement-based blend of powders to which only the site-addition of clean water shall be permitted. It must be chloride-free and must be formulated to prevent high exotherm and minimize thermal cracking

### Instruction for use

#### Preparation

Areas to be patched should be cut back to a depth of 15 mm and given a good mechanical key. Feather-edges must not be allowed. Surface should be brushed clean to remove loose material, dust and laitance. Grease, slime or mould growth should be removed by steam cleaning or high-pressure water jetting. A proprietary degreasing agent should be used for removal of light oil or grease contamination.

To seal leaks, crack openings must be chased out to approximately 20 mm square. The chase should always be undercut to avoid leaving a v-section. All loose material and debris should be removed.

#### Mixing

Renderoc Plug should be added to clean water in the following proportions:

One part clean water: 3 parts Renderoc Plug (measured by volume).

Mix to a stiff consistency in a suitable mixing drum or bucket, using a trowel or gloved hand. Due to the rapid set characteristics of the product, only prepare a quantity of mortar which can be placed within the prescribed set time.

#### Application

Trowel apply or hand-knead the mixed mortar in place, ensuring maximum contact with the substrate before the material sets. If being used to plug running water, Renderoc Plug should be used and held in place until the initial set is reached.

Note the minimum applied thickness of Renderoc Plug should be 15 mm.

#### Low temperature working

In cold conditions down to 1°C, the use of warm water (up to 20°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should be adopted. The material should not be applied when the substrate and/or air temperature is 1°C and falling. At 1°C static temperature or at 1°C and rising, the application may proceed.

# Fosroc® Renderoc Plug

---

## High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cooler water (down to 20°C) used for mixing.

## Cleaning

Renderoc Plug products should be removed from tools, equipment and mixers with clean water prior to the initial set. Cured material can only be removed mechanically

## Limitations

Renderoc Plug should not be used when the temperature is below 1°C and falling. If any doubts arise concerning application or substrate conditions, consult the local Fosroc office.

## Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

## Estimating

### Supply

---

**Renderoc Plug** : 1 KG tin, 4.5 KG tin, 25 KG bags

### Yield

---

**Renderoc Plug** : 0.5L/KG

---

## Storage

### Shelf life

Renderoc Plug has a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs. If stored at high temperatures and/or high humidity conditions the shelf life will be reduced.

## Precautions

### Health and safety

Renderoc Plug products contain cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes.

Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - **do not** induce vomiting.

### Fire

Renderoc Plug is non-flammable.

For further information, refer to the Product Material Safety Data Sheet.

\* Denotes the trademark of Fosroc International Limited

† See separate data sheet



### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

---

## Fosroc International

### Malaysia

**Fosroc Sdn. Bhd**

Tel : +60 3 5102 5660

Enquiry**malaysia@fosroc.com**

### Thailand

**Fosroc Thailand**

Tel : +66 2 136 9898

Enquiry**thailand@fosroc.com**

### Indonesia

**PT. Fosroc Indonesia**

Tel : +62 21 897 2103

Enquiry**indonesia@fosroc.com**

### Vietnam

**Fosroc Vietnam**

Tel : +82 241 3765 971

Enquiry**vietnam@fosroc.com**

### Singapore

**Fosroc Singapore**

Tel: +65 6665 3828

Enquiry**singapore@fosroc.com**

### Rest of Southeast Asia

**Fosroc Construction Chemical Pte Ltd**

Tel : +65 6665 3828

Enquiry**FGTAsia@fosroc.com**